



Thermal Insulation Products – Fibre Glass Tape

Fibre Glass Tapes

Sealumet insulation tapes are made of high-quality texturized E-glass with rigid selvages. Fiberglass tape is fabricated from high quality texturized fiberglass yarns that will not burn and will withstand continuous exposure to temperatures of 1000°F / 520°C. It resists most acids and alkalis and is unaffected by most bleaches and solvents.

They are particularly suitable for the insulation of pipes, wrapping of electrical cables and lining of switch boxes.



Thickness: 1.5mm up to 6mm
 Width: 10mm up to 200mm
 Weaving structure: Plain for thickness 1.5mm up to 3mm, twill for thickness 4mm up to 6mm
 Roll length: 30m or 50m

Thickness (mm)	Width (mm)	Roll length (m)	Yarn thickness (tex)		Yarn count(pc/cm)		Density (g/m ²)
			Warp	Weft	Warp	Weft	
1.5	10-200	30 or 50	1000	480	7.2	3.9	1100
2	10-200		1720	480	5.8	3	1400
2.5	13-200		2000	480	5.8	3	1750
3	13-200		2700	1200	4.8	1.9	2000
6	20-200		3600	1500	7	1.7	3800

Sealumet (Australia) Pty Limited
 Address: PO Box 2218,
 Warwick, Perth, WA-6065, Australia.
 Unit 2, Langar Way, Landsdale,
 Perth, WA 6065, Australia
 Tel: +618 6201 6153
 Fax: +618 9303 4560
www.sealumet.com

Sealumet Europe Limited
 Address: Unit A2 Lympe
 Distribution Park, Otterpool
 Lane,
 Hythe, Kent CT21 4LR
 Tel: +44 (0) 845 2426241
www.sealumet.com

Sealumet Singapore Pte Ltd
 Address: 2, Pioneer Sector 1,
 Singapore 628414
 Tel: +65 6265 6228
www.sealumet.com
www.cherrit.com.sg

Sealumet Middle East FZE
 Address: P O Box 53535
 Hamriya Free Zone,
 Sharjah, United Arab
 Emirates
 Tel: +971 6 557 5763
www.sealumet.com

Cherrit International (Far East) Pte Ltd
 Address: 2, Pioneer Sector 1,
 Singapore 628414
 Tel: +65 6265 6228
www.sealumet.com
www.cherrit.com.sg

DISCLAIMER

These data sheets are based on specifications, data and test results at time of publication. No guarantee as to completeness, accuracy or results is either expressed or implied. The suitability for an intended use is the responsibility of the user. As choice of material, method of application and site conditions are beyond our control we accept no liability for direct or consequential damages. Any material proved to be defective within the published shelf life* will be replaced. *From date of supply. Revision 1.0; 072018