

Rockwool 232

Product description

Rockwool 232 is a strong and rigid stone wool block and is especially developed for the fabrication of pre-shaped forms.

Application

Rockwool 232 Slabs fully comply with the requirements as set by EN 14303.

Product properties

	Performance											Norms	
Thermal conductivity	T (°C)	50	100	150	200	250	300	350	400				EN 12667
	λ (W/mK)	0,039	0,045	0,053	0,062	0,073	0,084	0,097	0,112				
Maximum Service Temperature	400 °C											EN 14706	
Reaction to fire	Euroclass A1											EN 13501-1	
Nominal density	90 kg/m ³											EN 1602	
Water Absorption	< 1 kg/m ²											EN 1609	
Water vapour diffusion resistance	μ = 1											EN 14303	
Air Flow Resistivity	> 40 kPa.s/m ²											EN 29053	
Designation code	MW EN 14303-T3-ST(+)-400-WS1											EN 14303	

